



香港城市大學  
City University of Hong Kong

專業 創新 胸懷全球  
Professional · Creative  
For The World

## CityU Scholars

### Nanostructured steels for advanced structural applications

Kong, H J; Yang, T; Zhang, T L; Cao, B X; Liu, C T

**Published in:**  
Materials Futures

**Published:** 01/03/2022

**Document Version:**  
Final Published version, also known as Publisher's PDF, Publisher's Final version or Version of Record

**License:**  
CC BY

**Publication record in CityU Scholars:**  
[Go to record](#)

**Published version (DOI):**  
[10.1088/2752-5724/ac376d](https://doi.org/10.1088/2752-5724/ac376d)

**Publication details:**  
Kong, H. J., Yang, T., Zhang, T. L., Cao, B. X., & Liu, C. T. (2022). Nanostructured steels for advanced structural applications. *Materials Futures*, 1(1), [013501]. <https://doi.org/10.1088/2752-5724/ac376d>

#### Citing this paper

Please note that where the full-text provided on CityU Scholars is the Post-print version (also known as Accepted Author Manuscript, Peer-reviewed or Author Final version), it may differ from the Final Published version. When citing, ensure that you check and use the publisher's definitive version for pagination and other details.

#### General rights

Copyright for the publications made accessible via the CityU Scholars portal is retained by the author(s) and/or other copyright owners and it is a condition of accessing these publications that users recognise and abide by the legal requirements associated with these rights. Users may not further distribute the material or use it for any profit-making activity or commercial gain.

#### Publisher permission

Permission for previously published items are in accordance with publisher's copyright policies sourced from the SHERPA RoMEO database. Links to full text versions (either Published or Post-print) are only available if corresponding publishers allow open access.

#### Take down policy

Contact [lbscholars@cityu.edu.hk](mailto:lbscholars@cityu.edu.hk) if you believe that this document breaches copyright and provide us with details. We will remove access to the work immediately and investigate your claim.

PERSPECTIVE • OPEN ACCESS

# Nanostructured steels for advanced structural applications

To cite this article: H J Kong *et al* 2022 *Mater. Futures* 1 013501

View the [article online](#) for updates and enhancements.

## You may also like

- [Properties and processing technologies of high-entropy alloys](#)  
Xuehui Yan, Yu Zou and Yong Zhang
- [Biomaterials for microfluidic technology](#)  
Zehao Chen, Zhendong Lv, Zhen Zhang et al.
- [Unleashing energy storage ability of aqueous battery electrolytes](#)  
Hongmei Tang, Zhe Qu, Yaping Yan et al.



## Perspective

# Nanostructured steels for advanced structural applications

H J Kong , T Yang ,  
T L Zhang , B X Cao   
and C T Liu\* 

*Department of Mechanical Engineering, Department of Material Science and Engineering, Hong Kong Institute for Advanced Study, City University of Hong Kong, Hong Kong, People's Republic of China*

## Abstract

This vision summarizes the recent advancement of nanostructured steels for advanced structural applications, foresees possible challenges and pinpoints future directions as well as opportunities in this new era of industrial revolution 4.0.

**Keywords:** nanostructured steels, extreme environments, advanced manufacturing, shape memory

The recent advancement of steel metallurgy has pushed the yield strength of the conventional steels to over 2 GPa together with an extraordinary ductility and toughness, especially important for the automotive and advanced aerospace industries where a light weight often comes to the priority [1, 2]. As we step into the new era of industrial revolution 4.0, the conventional alloy production has started to transform into a smarter manufacturing system focusing on the decentralized production with emphases on digitization, automation, and man-machine integrations. The current 2 GPa grade steels are developed based on the conventional steel production methodologies with complex processing routes such as hot working and cold rolling which are essentially impractical in today's advanced alloy production through additive manufacturing. The development of novel advanced steel design strategies is thus necessary. Advanced steels should also possess good mechanical properties in applications involving extreme operating conditions such as the nuclear fusion power plants and space exploration. Advanced steels that demonstrate a shape memory effect are also important in smart structural applications particularly in anti-seismic dampers and self-adjusting turbine blades. The continual development of advanced steels is crucial in pushing the social economy forward.

Conventionally, ultrahigh strength steels rely on heavy carbon additions which often lead them brittle and non-weldable [3–5]. Steels with a superior weldability is important in nowadays modern laser-based additive manufacturing. In the case of high carbon steels, the rapid cooling during the laser printing process can result in cold cracking [3]. On the other hand, nanostructured steels strengthened by densely dispersed nanoscale precipitates are highly weldable due to their low carbon content [6, 7], especially suitable for the modern additive manufacturing and re-manufacturing of structural parts of complex geometries in automotive, locomotive, and marine industries. Nanostructured steels are defined as advanced steels consisting of nanoscale features with a large interfacial area to volume ratio over  $0.04 \text{ nm}^{-1}$  [8]. Traditionally, the development of nanostructured steels mainly focuses on the grain refinement such as the production of nanostructured steels with nanometer-sized grains through severe plastic deformation [5, 9].

\* Author to whom any correspondence should be addressed.



Original content from this work may be used under the terms of the [Creative Commons Attribution 4.0 licence](https://creativecommons.org/licenses/by/4.0/). Any further distribution of this work must maintain attribution to the author(s) and the title of the work, journal citation and DOI.

Recently, by carefully tuning the chemistry of nanostructured steels, it is possible to develop a new class of 2 GPa grade low-carbon nanostructured steels with densely dispersed nanoscale precipitates [10–12]. Readers are advised to refer to the comprehensive reviews by Jiao *et al* [6] and Kong *et al* [7, 13] for the detailed processing, microstructure, and properties of this new class of nanostructured steels. Unfortunately, at this present stage, the precipitate strengthened steels produced by additive manufacturing have a relatively low yield strength in the range of  $\sim 1000$  MPa, possibly due to the formation of soft austenite or coarsening of microstructure due to the repetitive thermal cycling during the printing process [14, 15]. Besides, additive manufacturing does not involve the forging process as in the conventional manufacturing process, causing large grain sizes. Refined grain size is important in providing additional strengthening to nanostructured steels due to the Hall–Petch strengthening [16]. A new nanostructured steel recipe for advanced manufacturing is thus needed for an improved thermal stability and refined grain size.

Apart from the room temperature applications, nanostructured steels can be used in extreme environments, including the nuclear power plants and space vehicles that experience extreme temperature gradients. Literature indicates that highly disperse nanoscale precipitates in nanostructured steels can serve as vacancy traps and reduce swelling under irradiation conditions [17]. SpaceX has also started to shift to stainless steels for the construction of space vehicles for a cost reduction [18]. The current operating temperatures of nanostructured steels fall into around  $400\text{ }^{\circ}\text{C}$ – $500\text{ }^{\circ}\text{C}$ ; above which the precipitates will start to grow or dissolutionize [13]. At high temperatures, dislocations can climb over the precipitates easily, resulting in softening and creep deformations [19]. For the successful use of nanostructured steels in extreme environments, the discovery of new precipitates that can resist growth, dissolution, and impede dislocation motion at elevated temperatures is highly important. Moreover, nanostructured steels have a low impact toughness at cryogenic environments due to the segregation of embrittling elements at prior austenite grain boundaries after peak aging at  $400\text{ }^{\circ}\text{C}$ – $500\text{ }^{\circ}\text{C}$  [20]. Grain boundary engineering to control elemental segregations at the prior austenite grain boundaries together with the grain refinement can be a possible solution for enhancing the cryogenic toughness of nanostructured steels [7, 21–23].

Steels are crystallographically complex and can transform into various structures such as pearlite, bainite, martensite, and ferrite depending on the steel chemistries and thermal histories. As demonstrated in the Fe–Mn–Al [24], Fe–Ni–Co–Ti [25], Fe–Pd [26], and Fe–Pt [27] alloy systems, thermoelastic or reversible martensitic transformation which leads to a super-elasticity in iron-based shape memory alloys is possible with a careful composition adjustment. Recent studies [24, 25] indicate that a ‘right’ chemistry can induce nanoscale precipitation of coherent ordered particles, resulting in thermoelastic martensitic transformation with a low thermal hysteresis. Recent researchers [25, 28, 29] believe that these ordered precipitates with a high coherency with the matrix enhance the tetragonality of the Body Centered Tetragonal martensite while strengthening the martensite and therefore discourage slip in martensite, leading to a reversible mobile austenite/martensite interface during the martensitic transformation. Tanaka *et al* [25] discovered that the additions of Ta is important for obtaining the super-elasticity in the Fe–28Ni–17Co–11.5Al–2.5Ta alloy system as Ta additions increase the volume fraction of the ordered  $\gamma'$ -(Ni,Fe,Co)<sub>3</sub>(Al, Ta) precipitates. On the other hand, some researchers [30] argued that the precipitate size also plays an influential role in super-elasticity. A mechanistic understanding of the effects of alloying elements on the nanoscale precipitation and the resultant super-elasticity of various iron-based alloy systems

is certainly needed for the development of low-cost shape memory alloys with enhanced properties for cost-conscious applications.

In essence, the development of the nanostructured steels is still in its infancy stage. Revolutionary design strategies for advanced manufacturing of nanostructured steels with exceptional properties are further needed to satisfy the stringent requirements of advanced structural industries.

### Acknowledgments

Financial support from CityU Grant 9360161 and CityU 9380060 is gratefully acknowledged.

### ORCID iDs

H J Kong  <https://orcid.org/0000-0003-3508-661X>  
 T Yang  <https://orcid.org/0000-0003-4355-9210>  
 T L Zhang  <https://orcid.org/0000-0002-1877-8238>  
 B X Cao  <https://orcid.org/0000-0001-8221-1749>  
 C T Liu  <https://orcid.org/0000-0001-7888-9725>

### References

- [1] He B B, Hu B, Yen H W, Cheng G J, Wang Z K, Luo H W and Huang M X 2017 High dislocation density-induced large ductility in deformed and partitioned steels *Science* **357** 1029–32
- [2] Liu L, Yu Q, Wang Z, Ell J, Huang M X and Ritchie R O 2020 Making ultrastrong steel tough by grain-boundary delamination *Science* **368** 1347–52
- [3] Graville B A 1978 Cold cracking in welds in HSLA steels *Welding of HSLA (Microalloyed Structural Steels—Proc. Int. Conf. (Ohio))*
- [4] Garcia-Mateo C, Caballero F G and Bhadeshia H K D H 2003 Development of hard bainite *ISIJ Int.* **43** 1238–43
- [5] Li Y, Raabe D, Herbig M, Choi P, Goto S, Kostka A, Yarita H, Borchers C and Kirchheim R 2014 Segregation stabilizes nanocrystalline bulk steel with near theoretical strength *Phys. Rev. Lett.* **113** 106104
- [6] Jiao Z B, Luan J H, Miller M K, Chung Y W and Liu C T 2017 Co-precipitation of nanoscale particles in steels with ultra-high strength for a new era *Mater. Today* **20** 142–54
- [7] Kong H J, Jiao Z B, Lu J and Liu C T 2021 Low-carbon advanced nanostructured steels: microstructure, mechanical properties, and applications *Sci. China Mater.* **64** 1580–97
- [8] Bhadeshia H K D H 2013 The first bulk nanostructured metal *Sci. Technol. Adv. Mater.* **14** 014202
- [9] Halfa H 2014 Recent trends in producing ultrafine grained steels *J. Miner. Mater. Charact. Eng.* **2** 428–69
- [10] Jiao Z B, Luan J H, Miller M K and Liu C T 2015 Precipitation mechanism and mechanical properties of an ultra-high strength steel hardened by nanoscale NiAl and Cu particles *Acta Mater.* **97** 58–67
- [11] Niu M C, Zhou G, Wang W, Shahzad M B, Shan Y and Yang K 2019 Precipitate evolution and strengthening behavior during aging process in a 2.5 GPa grade maraging steel *Acta Mater.* **179** 296–307
- [12] Jiang S *et al* 2017 Ultrastrong steel via minimal lattice misfit and high-density nanoprecipitation *Nature* **544** 460–4
- [13] Kong H J and Liu C T 2018 A review on nano-scale precipitation in steels *Technologies* **6** 36
- [14] Kurnsteiner P, Wilms M B, Weisheit A, Gault B, Jagle E A and Raabe D 2020 High-strength Damascus steel by additive manufacturing *Nature* **582** 515–9
- [15] Abrahams R A 2019 Low alloy high performance steel USA Patent US20160369362A1
- [16] Chen R, Kong H J, Luan J H, Wang A D, Jiang P and Liu C T 2020 Effect of external applied magnetic field on microstructures and mechanical properties of laser welding joint of medium-Mn nanostructured steel *Mater. Sci. Eng. A* **792** 139787
- [17] Zhang Z W, Liu C T, Wang X L, Miller M K, Ma D, Chen G, Williams J R and Chin B A 2012 Effects of proton irradiation in nanocluster precipitation in ferritic steel containing fcc alloying additions *Acta Mater.* **60** 3034–46
- [18] Wall M 2020 SpaceX's Starship will soon be made of different stuff *Space.com* (available at: [www.space.com/spacex-starship-new-stainless-steel-alloy.html](http://www.space.com/spacex-starship-new-stainless-steel-alloy.html))

- [19] Song G *et al* 2015 Ferritic alloys with extreme creep resistance via coherent hierarchical precipitates *Sci. Rep.* **5** 16327
- [20] Kong H J, Xu C, Bu C C, Da C, Luan J H, Jiao Z B, Chen G and Liu C T 2019 Hardening mechanisms and impact toughening of a high-strength steel containing low Ni and Cu additions *Acta Mater.* **172** 150–60
- [21] Kuzmina M, Herbig M, Ponge D, Sandlobes S and Raabe D 2015 Linear complexions: confined chemical and structural states at dislocations *Science* **349** 1080–3
- [22] Kuzmina M, Ponge D and Raabe D 2015 Grain boundary segregation engineering and austenite reversion turn embrittlement into toughness: example of a 9 wt% medium Mn steel *Acta Mater.* **86** 182–92
- [23] Armstrong R W 2017 Dislocation pile-ups, strength properties and fracturing *Rev. Adv. Mater. Sci.* **48** 1–12
- [24] Omori T, Ando K, Okano M, Xu X, Tanaka Y, Ohnuma I, Kainuma R and Ishida K 2011 Superelastic effect in polycrystalline ferrous alloys *Science* **33** 68–71
- [25] Tanaka Y, Himuro Y, Kainuma R, Sutou Y, Omori T and Ishida K 2010 Ferrous polycrystalline shape-memory alloy showing huge superelasticity *Science* **327** 1488–90
- [26] Oshima R and Sugiyama M 1982 Martensite transformations in Fe-Pd alloys *J. Phys. Colloq.* **43** 383–8
- [27] Dunne D P and Wayman C M 1973 The effect of austenite ordering on the martensite transformation in Fe-Pt alloys near the composition Fe<sub>3</sub>Pt: I. Morphology and transformation characteristics *Metall. Trans.* **4** 137–45
- [28] Kajiwara S 1999 Characteristic features of shape memory effect and related transformation behavior in Fe-based alloys *Mater. Sci. Eng. A* **273–275** 67–88
- [29] Maki T, Kobayashi K, Minato M and Tamura I 1984 Thermoelastic martensite in an ausaged Fe-Ni-Ti-Co alloy *Scr. Metal.* **18** 1105–9
- [30] Tseng L W, Ma J, Hornbuckle B C, Karaman I, Thompson G B, Luo Z P and Chumlyakov Y I 2015 The effect of precipitates on the superelastic response of [100] oriented FeMnAlNi single crystals under compression *Acta Mater.* **97** 234–44